


PRODUCT

ESD Cellulose Tape

TECHNICAL DATASHEET

DESCRIPTION

ESD tape made from a natural transparent, antistatic, cellulose tape with an environmentally friendly hot glue adhesive. This tape is designed to be used within EPAs for packaging bags and boxes and for any other packaging requirements.

Backing Material: Natural transparent cellulose
 Thickness: $27 \pm 0.66\mu\text{m}$ ($40\text{g}/\text{m}^2$)

Adhesive: Environmentally friendly hot glue
 Thickness: $20 \pm 1\mu\text{m}$ ($20\text{g}/\text{m}^2$)

FEATURES

- Available in 2 widths, 25mm and 50mm
- Each roll is 66 meters long

PRODUCT CODE	DESCRIPTION	SIZE	QUANTITY
054-0123	ESD Cellulose Tape	25mm x 66m	Each
054-0124	ESD Cellulose Tape	50mm x 66m	Each

TECHNICAL INFORMATION

MATERIAL CONTENT	SUBSTANCE NAME	SUBSTANCE RATIO
Transparent Cellulose	$(\text{C}_6\text{H}_{10}\text{O}_5)_n$	53.33%
Softener	$\text{C}_3\text{H}_8\text{O}_3$	8%
Water	H_2O	5.33%
TPE	SIS	21%
Tackyfying Resin	C5Petroleum Resin	5%
Tackyfying Resin	Hydrogenated Rosin	4%
Softener	Liquid Paraffin	1.67%
Viscosity Modifier	Paraffin wax and hydrocarbon wax	0.17%
Flame Retardant	Chlorinated Paraffin	1.5%

To request a quotation or for more information, please call **+44 (0)1473 836200**
 email info@antistat.co.uk or visit www.antistat.co.uk

IMPORTANT: This data sheet and its contents (the "Information") belong to Antistat or are licensed to it. No licence is granted for the use of it other than for information purposes in connection with the products to which it relates. No licence of any intellectual property rights is granted. The Information is subject to change without notice and replaces all data sheets previously supplied. The Information supplied is believed to be accurate but Antistat assumes no responsibility for its accuracy or completeness, any error in or omission from it or for any use made of it. Users of this data sheet should check for themselves the Information and the suitability of the products for their purpose and not make any assumptions based on information included or omitted. Liability for loss or damage resulting from any reliance on the Information or use of it (including liability resulting from negligence or where Antistat was aware of the possibility of such loss or damage arising) is excluded. © 2024 Antistat.

PHYSICAL PROPERTIES

TEST ITEMS	UNIT	AVERAGE VALUE	TEST RESULT
Average Thickness	µm	47	48
180°C Peel Strength	N/cm	≥2.5	6.1
90°C Peel Strength	N/cm	≥2.0	5.3
Initial Adhesion	N	≥8	15.8
Holding Adhesion	h	≥24	48
Tensile Strength - longitudinal	N/cm	≥15	38.5
Elongation at break - longitudinal	%	≥8	21.3
Unwinding Force at Low Speed	N/cm	≥0.5	0.082
Surface Resistance	ohms	10 ⁸ -10 ¹⁰	10 ⁸ -10 ¹⁰
Tribocharging	V	Less than 100	Less than 100

APPLICATION CONDITIONS

Recommended Using Environment	Parameter
Temperature	10-100°C
Humidity	45-75%
Storage Temperature	<50°C
Storage Humidity	Keep sealed away from light
Storage Time	12 months

SPECIFICATIONS

CONTENT	MEASUREMENT	TESTING VALUE
Thickness	µm	47
Width	mm	25/50
Length	m	66
Paper Core	mm	76
Weight	g/m ²	60

To request a quotation or for more information, please call **+44 (0)1473 836200**
 email info@antistat.co.uk or visit www.antistat.co.uk

IMPORTANT: This data sheet and its contents (the "Information") belong to Antistat or are licensed to it. No licence is granted for the use of it other than for information purposes in connection with the products to which it relates. No licence of any intellectual property rights is granted. The Information is subject to change without notice and replaces all data sheets previously supplied. The Information supplied is believed to be accurate but Antistat assumes no responsibility for its accuracy or completeness, any error in or omission from it or for any use made of it. Users of this data sheet should check for themselves the Information and the suitability of the products for their purpose and not make any assumptions based on information included or omitted. Liability for loss or damage resulting from any reliance on the Information or use of it (including liability resulting from negligence or where Antistat was aware of the possibility of such loss or damage arising) is excluded. © 2024 Antistat.