


**PRODUCT**

# Clear Carrier Tape with Antistatic Cover Tape

**TECHNICAL DATASHEET**
**DESCRIPTION**

The following table outlines the typical values for dissipative clear polystyrene product(s) produced by Antistat.



PROPERTY		TYPICAL VALUE	UNIT	TEST METHOD
Specific Gravity		1.06	g/cm <sup>3</sup>	ASTM D792
Tensile Strength @ Peak	MD	390	Kg/cm <sup>2</sup>	ASTM D638
	TD	300	Kg/cm <sup>2</sup>	ASTM D638
Elongation	MD	50	%	ASTM D638
	TD	40	%	ASTM D638
Heat Distortion Temp		≥75	°C	ASTM D648
Light Transmittance (0.3mm sheet)		90 ± 5	%	ASTM D1003
Haze (0.3mm sheet)		10 ± 5	%	ASTM D1003
Length		450mm		


PRODUCT CODE	SIZE	QUANTITY
029-1090	8mm	500
029-1091	12mm	500
029-1092	16mm	250
029-1093	24mm	250
029-1117	32mm	250
029-1118	44mm	250

To request a quotation or for more information, please call **+44 (0)1473 836200**  
 email [info@antistat.co.uk](mailto:info@antistat.co.uk) or visit [www.antistat.co.uk](http://www.antistat.co.uk)

IMPORTANT: This data sheet and its contents (the "Information") belong to Antistat or are licensed to it. No licence is granted for the use of it other than for information purposes in connection with the products to which it relates. No licence of any intellectual property rights is granted. The Information is subject to change without notice and replaces all data sheets previously supplied. The Information supplied is believed to be accurate but Antistat assumes no responsibility for its accuracy or completeness, any error in or omission from it or for any use made of it. Users of this data sheet should check for themselves the Information and the suitability of the products for their purpose and not make any assumptions based on information included or omitted. Liability for loss or damage resulting from any reliance on the information or use of it (including liability resulting from negligence or where Antistat was aware of the possibility of such loss or damage arising) is excluded. © 2024 Antistat.

### COVER TAPE STRUCTURE

The Seal-Pack Heat Seal Activated Cover Tape is manufactured using Antistatic Polyethylene Terephthalate Film and other proprietary adhesive materials.



### COVER TAPE PROPERTIES

PROPERTY	ASTM METHODS	UNIT	TYPICAL VALUE
PERFORMANCE			
Thickness	Micro Gauge	um	55 +/- 5
MECHANICAL			
Tensile Strength	D638	Kgf/cm <sup>2</sup>	650 +/- 50
Tensile Elongation	D638	%	75 +/- 5
Tear Strength	D1004	Kgf/cm	100 Min
Luminous Transmittance	D1003	%	90 +/- 5
Hazeness	D1003	%	10 +/- 2
ELECTRICAL			
Surface Resistance	ANSI/ESD STM11.13 - 2021	Ohms	10 <sup>6~9</sup>
Testing carried out at 23°C at both 12% and 50% RH.			

To request a quotation or for more information, please call **+44 (0)1473 836200**  
email [info@antistat.co.uk](mailto:info@antistat.co.uk) or visit [www.antistat.co.uk](http://www.antistat.co.uk)

IMPORTANT: This data sheet and its contents (the "Information") belong to Antistat or are licensed to it. No licence is granted for the use of it other than for information purposes in connection with the products to which it relates. No licence of any intellectual property rights is granted. The Information is subject to change without notice and replaces all data sheets previously supplied. The Information supplied is believed to be accurate but Antistat assumes no responsibility for its accuracy or completeness, any error in or omission from it or for any use made of it. Users of this data sheet should check for themselves the Information and the suitability of the products for their purpose and not make any assumptions based on information included or omitted. Liability for loss or damage resulting from any reliance on the information or use of it (including liability resulting from negligence or where Antistat was aware of the possibility of such loss or damage arising) is excluded. © 2024 Antistat.